



OLYMP-X™ SYSTEM

The Horner Olymp-X System is a flooring system that has been both IAAF and DIN (2001) certified. Olymp-X has been specifically designed for dual-durometer, high performance track and fieldhouse applications. A full-color, vulcanized rubber surface provides extended longevity and high levels of comfort and shock absorption.

PART 1-GENERAL

1.1 DESCRIPTION

- A. This document specifies the complete installation of a urethane surface system designed for multiple sport use, as formulated by Horner Flooring Company.
- B. Related work specified under other sections.
 - 1. CONCRETE SUBFLOORS
 - a. The general contractor shall furnish and install the concrete subfloors, depressing the slab sufficiently to accommodate the floor system. The slab shall be steel troweled and finished smooth to a tolerance of 1/8" (3mm) in any 10' (3m) radius. High spots shall be ground level, and low spots filled in with approved leveling compound. **No concrete curing or hardening agents shall be applied to concrete subfloor.**
 - 2. MEMBRANE WATERPROOFING
 - a. Concrete subfloors on or below grade shall be adequately waterproofed beneath and at the perimeter walls and on earth side of below grade walls. It is the responsibility of the engineer to determine the extent of this need.

1.2 QUALITY ASSURANCE

- A. Manufacturer Qualifications:
 - 1. Manufacturer of resilient flooring shall be a firm specializing in manufacturing products specified in this section. Manufacturer must be in the sports flooring business a minimum of 10 years.
- B. Installer Qualifications:
 - 1. The complete installation of the flooring system, as described in the scope of these specifications, shall be carried out by an experienced installer (Flooring Contractor), and the work shall be performed in accordance with most recent installation instructions of the manufacturer.
- C. Pre-Installation Meetings:
 - 1. Conduct pre-installation meeting to verify project requirements, substrate conditions, manufacturer's instructions, and manufacturer's warranty requirements.

1.3 SUBMITTALS

- A. Specifications - Submit Horner specification sheets.
- B. Samples - Submit color, texture, thickness, or finish samples of the specified system as needed and requested by the customer or architect.
- C. Maintenance Literature – Upon completion of floor installation, send to owner, attendants, or individuals in charge and responsible for the upkeep of the building a Horner Synthetic Flooring Care and Maintenance Guide. These instructions shall be followed. Any variations, deviations, or substitutions shall be submitted to Horner for approval.

1.4 DELIVERY AND STORAGE

- A. Comply with manufacturer's ordering instructions and lead time requirements to avoid unnecessary storage and construction delays.
- B. Delivery of materials shall not be completed until the site and climate are ready for installation.
- C. The general contractor shall provide a secure, clean, dry location for storage of materials at a temperature range of 50°F (10°C) to 85°F (30°C).
 - 1. Outdoor Storage
 - a. If materials are to be stored outside, they must be fully protected from moisture by a covering with 10 mil polyethylene film and a tarpaulin.
 - b. All materials stored outside shall be inspected by the installer/dealer for moisture contamination before installation.

1.5 WARRANTY

- A. Horner Flooring Company hereby warrants the OLYMP-X SYSTEM flooring materials to be free from manufacturing defects for a period of one year from the date of substantial completion of the floor.

1.6 WORKING CONDITIONS

- A. Synthetic materials specified herein shall not be installed until all masonry, painting, plaster, tile, marble and terrazzo work is completed, and overhead mechanical trades and painters have finished in the synthetic floor areas. The building shall be enclosed and water tight.

- B. Permanent heat, light, and ventilation shall be installed and operating prior to and after installation. The general contractor shall provide an area where the stored materials can be maintained at a minimum of 55° F (13° C) and under 50% relative humidity. Ideal installation and storage conditions are the same as those which will prevail when building is occupied.
- C. Subfloors shall be clean, dry and free from dirt, dust, oil, grease, paint, alkali, concrete curing agents, hardening and parting compounds, old adhesive residue or other foreign materials. Moderate room temperature of 65° F (18° C) or more and 35% relative humidity or less shall be maintained for a week prior to, during and for 72 hours after installation.
- D. Flooring installation shall not begin until all sub-contract work which would cause damage, dirt, dust or interruption of normal installation pace is completed. The installation area shall be closed to all traffic and activity for a period to be set by the flooring contractor.
- E. Moisture content of the concrete slab must not exceed 4%.
- F. Environmental Limitations
 - 1. Comply with requirements of athletic flooring material supplier.
 - 2. Adhere to all MSDS requirements for materials employed in the work. Protect all persons from exposure to hazardous materials.
- G. After synthetic floors are installed and the game lines have been painted, the floor area is to be kept locked by general contractor for a minimum of 72 hours to allow curing time for system. No other trades or personnel are allowed on floor until accepted by the owner in writing.

PART 2-PRODUCTS

2.1 MATERIALS

- A. All polyurethane components shall be non-hazardous and not contain ANY lead, mercury, nor any heavy metals, PCB or formaldehyde and shall be supplied by Horner Flooring Company
- B. Horner Olymp-X™ flooring shall be rubber roll goods with fieldhouse or track embossing.
 - 1. Choose from nine (9) colors.
 - 2. Roll options (materials shall be a solid, consistent color and thickness throughout)
 - a. Specify roll thickness:
 - i. 3/16", 1/4", 5/16", 3/8", or 1/2". (5mm, 6mm, 8mm, 10mm, or 13mm)
 - b. Specify roll width:
 - i. 3'-4' (0.9m-1.22m)
 - c. Specify roll length:
 - i. 30'-75' (9m-23m) total length.
 - ii. Total roll length may consist of multiple pieces.

This is determined by a combination of thickness, width, and total roll weight.
- C. Horner Olymp-X shall meet the following minimum physical properties in accordance with ASTM standards:
 - 1. Physical properties are in accordance with ASTM D3182, Standard practice for Rubber Materials, equipment and procedures for mixing standard compounds and preparing standard vulcanized sheets.
 - 2. Preparation of pieces for test from other than standard vulcanized sheets are in accordance with ASTM D3183 standard recommended practice.
 - 3. Test results are based on compound cured according to ASTM procedures. Actual manufactured product may vary.

a. Elongation %(+/-50)	350%	ASTM D412
b. Tensile Strength (+/-100)	800 psi – 1000psi	ASTM D412
c. 100% Modulus (+/-25)	275 psi	ASTM D412
d. 300% Modulus (+/-25)	650 – 750	ASTM D412
e. Hardness Shore A (+/-5)	50-55	ASTM D395
f. Compression Set % (72 Hrs @ 70 °F (21 °C) 90%-98% Recovery)	17% recuperation	ASTM D395
g. Tear, Die-C lbs/in (+/-10)	130-140psi	ASTM D624
h. Ozone Exposure (Bent Loop Exposure)	No Cracks/Change	
i. Spike Traffic	Yes	
j. NBS Abrasion % of Control NBS Method	58	
k. Coefficient of Friction	Dry Wet	
	Leather .8µk .92µk	
	Rubber .96µk	
- D. Horner Olymp-X urethane adhesive shall be approved by manufacturer. Use of non-approved adhesive shall void any warranty.
- E. Horner Game Line Paint is a two component, high solids, polyurethane, mat line paint. It comes in seven (7) standard colors.
- F. OPTION: Vinyl wall base 4" (102mm) high; select color: black or brown.

PART 3-EXECUTION

3.1 INSPECTION

- A. Surface Inspection
 - 1. Refer to specific Horner substrate specifications.
 - 2. The existing system shall be inspected with the owner to determine if repairs are needed. The installer shall perform tests for moisture and adhesion prior to application.
 - a. Report adverse conditions to the owner or his/her representative in writing.
 - b. Report any discrepancies or repairs needed to the general contractor.
- B. The substrate surface shall be broom cleaned by general contractor.
- C. Installer shall document all working conditions provided in general specifications before installation begins.

3.2 INSTALLATION

- A. Unroll product and allow to relax. Do not cut product to final dimensions until laid into adhesive.
 - 1. Thoroughly mix the two-component polyurethane adhesive and apply directly to the concrete subfloor with a 1/8" (3mm) notched trowel per manufacturer's instructions.
 - 2. Install product into freshly applied adhesive.
 - a. End seams will be single cut.
 - b. Edge seams will be overlapped and snapped into place to ensure a tight seam.
 - 3. Do not allow compression fit at any seams. Roll product with a medium sized steel roller to remove any trapped air. Wipe away any adhesive that oozes between the seams with wood alcohol.
 - 4. All seams must be weighted in place. Leave weights in place for a minimum of 12 hours.
- B. Game Lines
 - 1. Use only high quality masking tape approved by manufacturer.
 - 2. Thoroughly mix two-component game line paint.
 - 3. Provide game lines as indicated with specifications and governing bodies.
- C. OPTION: Install vinyl base by anchoring to walls with base cement.
- D. Remove all excess and waste materials from the area of work. Dispose of empty containers in accordance with federal and local statutes.

3.3 PROTECTION

- A. No traffic or other trades shall be allowed on the surface for a period of one week following installation to allow for complete cure of the finish.
- B. No smoking, open flames, or sparks from electrical equipment or other sources shall be permitted during application of materials

3.4 MAINTENANCE

- A. Upon completion of floor installation, the owner, attendants, or individuals in charge of and responsible for the upkeep of the building are to see that the care and maintenance instructions of the Horner Synthetic Flooring Care and Maintenance Guide are followed.